

## ABSTRACT

Glass is provided so as to have high visible transmission and/or fairly clear or neutral color. In certain example embodiments of making glass according to examples of the invention, the glass batch may include a base glass (e.g., soda lime silica base glass) and, in addition, by weight percentage:

total iron (expressed as $\text{Fe}_2\text{O}_3$ ):	0.01 to 0.30 %
erbium oxide (e.g., $\text{Er}_2\text{O}_3$ ):	0.01 to 0.30 %
cerium oxide (e.g., $\text{CeO}_2$ ):	0.005 to 0.30 %.

Optionally, neodymium oxide (e.g.,  $\text{Nd}_2\text{O}_3$ ) may also be provided in the glass in certain example embodiments. In other embodiments, the cerium oxide may be replaced with or supplemented by  $\text{NaNO}_3$  or some other nitrate(s) as an oxidizer.